



HAYCARB
Activated carbon solutions

Haycarb Air Series

Personal Respirators & Face Masks

RCPF 1002 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt) (Base)	Min: 65	ASTM
Iodine Number (mg/g) (Base)	Min: 1200	ASTM
Apparent Density (g/cc)	Min: 0.47	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
pH	9-11	ASTM
Hardness No	Min: 97	ASTM
Particles size 30x60 ASTM mesh		
> 30 mesh (0.60 mm) (% by wt)	Max: 5	ASTM
30x60 mesh (0.60 mm x 0.25 mm) (% by wt)	Min: 90	ASTM
< 60 mesh (0.25 mm) (% by wt)	Max: 5	ASTM

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com