

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

Haycarb Food & Beverage Series Fruit Juices

RFBB 1012 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 50	ASTM
Iodine Number (mg/g)	Min: 1050	ASTM
Apparent Density (g/cc)	Min: 0.52	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
pH	8-11	ASTM
Hardness No	Min: 98	ASTM
Particles size 18x40 ASTM mesh		
> 18 mesh (1.00 mm) (% by wt)	Max: 5	ASTM
18X40 mesh (1.00 mm x 0.425 mm) (% by wt)	Min: 90	ASTM
< 40 mesh (0.425 mm) (% by wt)	Max: 5	ASTM



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com