

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

Haycarb Water Series

Carbonated Drinks and Alcohols

RFBB 3002 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 55	ASTM
Iodine Number (mg/g)	Min: 1100	ASTM
Apparent Density (g/cc)	Min: 0.50	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
pH	8-11	ASTM
Hardness No.	Min: 98	ASTM
Particles size 14x45 US mesh		ASTM
> 14 mesh (1.40 mm) (% by wt)	Max: 5	ASTM
14x45 (1.40 mm x 0.355 mm) (% by wt)	Min: 90	ASTM
< 45 mesh (0.355 mm) (% by wt)	Max: 5	ASTM



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com