

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

Haycarb Food & Beverage Series Food Oils

RFBO 1005 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 75	ASTM
Iodine Number (mg/g)	Min: 1300	ASTM
Moisture (% wt/wt)	Max: 8	ASTM
Ash (% wt)	Max: 5	ASTM
pH	9-11	ASTM
Particles size 40x325 US mesh		WET SIEVE
> 40 mesh (0.425 mm) (% by wt)	Max: 5	
40x325 (0.425 mm x 0.045 mm) (% by wt)	Min: 90	
< 325 mesh (0.045 mm) (% by wt)	Max: 5	



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com