



**HAYCARB**  
Activated carbon solutions

## Haycarb Air Series

### Pressure Swing Adsorption

#### RIAG 1001 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 45	ASTM
Iodine Number (mg/g)	Min: 1000	ASTM
Apparent Density (g/cc)	Min: 0.53	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
Hardness No.	Min: 98	ASTM
Particles size 3S		
Diameter (mm)	3.0	
Length (mm)		

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: [www.nsf.org/certified/DWTU](http://www.nsf.org/certified/DWTU)  
Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



[www.haycarb.com](http://www.haycarb.com)