



HAYCARB
Activated carbon solutions

Haycarb Water Series

Desalination Systems

RIWD 1002 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 50	ASTM
Iodine Number (mg/g)	Min: 1050	ASTM
Apparent Density (g/cc)	Min: 0.52	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
pH	9-11	ASTM
Hardness No	Min: 98	ASTM
Particles size 20x50 US mesh		ASTM
> 20 mesh (0.85 mm) (% wt/wt)	Max: 5	
20x50 mesh (0.85 mmx 0.30 mm) (% wt/wt)	Min: 90	
< 50 mesh (0.30 mm) (% wt/wt)	Max: 5	

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU
Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com