



**HAYCARB**  
Activated carbon solutions

## Haycarb Water Series

### Dialysis

#### RMPB 1001 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 55	ASTM
Iodine Number (mg/g)	Min: 1100	ASTM
Apparent Density (g/cc)	Min: 0.52	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 1	ASTM
pH	6-8	ASTM
De chlorination Half Value	Min: 2.5	DIN
Particles size 12x40 US mesh		ASTM
> 12 mesh ( 1.70 mm ) (% wt/wt)	Max: 5	
12x40 mesh ( 1.70 mmx 0.425 mm ) (% wt/wt)	Min: 90	
< 40 mesh ( 0.425 mm ) (% wt/wt)	Max: 5	



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: [www.nsf.org/certified/DWTU](http://www.nsf.org/certified/DWTU)  
Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



[www.haycarb.com](http://www.haycarb.com)