



**HAYCARB**  
Activated carbon solutions

## Haycarb Gold Series

### Rare Metal Recovery

#### RPMR 1004 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min:55	ASTM
Iodine Number (mg/g)	Min: 1100	ASTM
Apparent Density (g/cc)	Min: 0.50	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 1	ASTM
pH	6-8	ASTM
Hardness No.	Min: 99	ASTM
Particles size 8x35 US mesh		ASTM
> 8 mesh (2.36 mm) (% by wt)	Max: 5	ASTM
8x35 mesh (2.36 mm x 0.50 mm) (% by wt)	Min: 90	ASTM
< 35 mesh (0.50 mm) (% by wt)	Max: 5	ASTM



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: [www.nsf.org/certified/DWTU](http://www.nsf.org/certified/DWTU)

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



[www.haycarb.com](http://www.haycarb.com)