



HAYCARB
Activated carbon solutions

Haycarb Air Series

Military Applications

RPPM 3007 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt) (Base)	Min: 85	ASTM
Iodine Number (mg/g) (Base)	Min: 1400	ASTM
Apparent Density (g/cc)	Min: 0.41	ASTM
Moisture (% wt/wt)	Max: 2.5	ASTM
Ash (% wt)	Max: 3.5	ASTM
pH	9-11	ASTM
Hardness No	Min: 97	ASTM
Particles size 6x16 ASTM mesh		
> 6 mesh (3.35 mm) (% by wt)	Max: 5	ASTM
6X16 mesh (3.35 mm x 1.18 mm) (% by wt)	Min: 90	ASTM
< 16 mesh (1.18 mm) (% by wt)	Max: 5	ASTM

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com