



HAYCARB
Activated carbon solutions

Haycarb Air Series

Solvent Recovery

RSRB 1002 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 60	ASTM
Iodine Number (mg/g)	Min: 1150	ASTM
Apparent Density (g/cc)	0.43	ASTM
Moisture (% wt/wt)	Max: 3	ASTM
Ash (% wt)	Max: 5	ASTM
pH	6-8	ASTM
Hardness No.	Min: 99	ASTM
Benzene Adsorption (% by wt) (Full Saturation)	Min: 38	ASTM
Particles size 4S		
Diameter (mm)	4.0	
Length (mm)	6.0-8.0	

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com