



HAYCARB
Activated carbon solutions

Haycarb Water Series

Chloramine Removal

RWAC 1008 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 45	ASTM
Iodine Number (mg/g)	Min: 1000	ASTM
Apparent Density (g/cc)	Min: 0.50	ASTM
Moisture (% wt/wt)	Max: 4	ASTM
Ash (% wt)	Max: 3	ASTM
pH	7-10	ASTM
Catalytic Activity (Temp Increase) (°C)	20	HC method
Particles size 40x100 US mesh		ASTM
> 40 mesh (0.425 mm) (% by wt)	Max: 5	ASTM
40x100 mesh (0.425 mm x 0.150 mm) (% by wt)	Min: 90	ASTM
< 100 mesh (0.150 mm) (% by wt)	Max: 5	ASTM

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com