



**HAYCARB**  
Activated carbon solutions

## Haycarb Water Series

### Industrial Water Filters

#### RWAP 1068 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 50	ASTM
Iodine Number (mg/g)	Min: 1050	ASTM
Apparent Density (g/cc)	Min: 0.48	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
pH	9-11	ASTM
Hardness No	Min: 98	ASTM
Particles size 14x45 US mesh		ASTM
> 14 mesh ( 1.40 mm ) (% wt/wt)	Max: 5	
14x45 mesh ( 1.40 mmx 0.355 mm ) (% wt/wt)	Min: 90	
< 45 mesh ( 0.355 mm ) (% wt/wt)	Max: 5	



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: [www.nsf.org/certified/DWTU](http://www.nsf.org/certified/DWTU)  
Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



[www.haycarb.com](http://www.haycarb.com)