



HAYCARB
Activated carbon solutions

Haycarb Water Series

Bacteriostatic Filters

RWAP 6006 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt) (Base)	Min: 50	ASTM
Iodine Number (mg/g) (Base)	Min: 1050	ASTM
Apparent Density (g/cc)	Min: 0.50	ASTM
Moisture (% wt/wt)	Max: 10-15	ASTM
Ash (% wt)	Max: 3	ASTM
pH	9-11	ASTM
Hardness Number	Min: 98	ASTM
Silver Loading (% by wt)	Min: 0.1	ASTM
Particles size 12x30 US mesh		
> 12 mesh (1.70 mm) (% by wt)	Max: 5	LASER
12x30 mesh (1.70 mm x 0.60 mm) (% by wt)	Min: 90	LASER
< 30 mesh (0.60 mm) (% by wt)	Max: 5	LASER

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com