



HAYCARB
Activated carbon solutions

Haycarb Water Series

Bacteriostatic Filters

RWAP 6026 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt) (Base)	Min: 60	ASTM
Iodine Number (mg/g) (Base)	Min: 1150	ASTM
Apparent Density (g/cc)	Min: 0.45	ASTM
Moisture (% wt/wt)	Max: 10-15	ASTM
Ash (% wt)	Max: 4	ASTM
pH	Test & Report	ASTM
Hardness Number	Min: 97	ASTM
Silver Loading (% by wt)	Min: 0.4	ASTM
Particles size 18x40 US mesh		ASTM
> 18 mesh (1.00 mm) (% by wt)	Max: 5	
18x40 mesh (1.00 mm x 0.425 mm) (% by wt)	Min: 90	
< 40 mesh (0.425 mm) (% by wt)	Max: 5	

This product is also available in below particle sizes



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com